

AERODISP® W 7520

DESCRIPTION

AERODISP® W 7520 is a 20% dispersion of hydrophilic AEROSIL® fumed silica with slightly alkaline pH-value.

KEY BENEFITS

- water-based dispersion
- fully dispersed
- easy to incorporate

GRAPHICAL BAR

Anti-settling



Anti-sagging



Corrosion resistance



SUITABILITY

waterborne



solventborne



radiation-curing



1-pack coatings



2-pack coatings



● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- General industrial coatings
- Decorative coatings
- Plastic coatings

TECHNICAL DATA

pH-value	9.5 - 10.5
SiO₂ content	19-20 %
viscosity	Max. 100 mPas

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 5 - 10 %

HANDLING & STORAGE

Depending on the region, the product is available in 60 kg container, 220 kg drums and 1000 kg intermediate bulk containers (IBC's). All dispersions must be protected from extrem heat and frost. The product should be used within 12 months from date of production.

MSDS & REGULATORY INFORMATION



This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com