

DESCRIPTION

CARBOWET® 109 is a non-ionic wetting additive that provides additional dispersing properties. Wets all kinds of pigments. Was designed as alternative to APEs with a HLB-value around 13.

KEY BENEFITS

- fast pigment and substrate wetting
- cost efficient
- 100% active and low viscous liquid

SUITABILITY

waterborne	solventborne
●	●
2-pack 100%	radiation-curing
●	●
direct grind	resin-containing pigment concentrates
●	●
resin-free pigment concentrates	
●	

● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Architectural paints
- Printing Inks
- General industrial coatings
- Wood coatings

TECHNICAL DATA

active matter content	100 %
appearance	clear, pale yellow liquid
chemical description	alcohol ethoxylate
HLB	13

SOLUBILITY

Water	Ethanol
●	●
TPGDA	Acetone
●	●
Butylacetate	Mineral Spirits
●	●

● not soluble ● partly soluble ● soluble

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 1.0 - 3.0 %

PROCESSING INSTRUCTIONS

Add before grinding.

HANDLING & STORAGE

Keep away from direct sunlight. Overheating of an ethoxylate stored under air should be avoided. When an ethoxylate is vigorously mixed in the presence of air or oxygen at temperatures > 125°F (> 50°C), it can degrade product quality. Storage under an inert atmosphere is recommended. Keep containers tightly closed in a dry, cool, and well-ventilated place. Product is freeze-thaw stable; if it phase separates or freezes at colder temperatures, warm container to 40°C and mix thoroughly before use.

MSDS & REGULATORY INFORMATION

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com