

Compatibilizer

TEGO® ColorAid 7060

KEY BENEFITS

- improves color acceptance of universal colorants in alkyds
- very low influence on drying time
- suitable for all types of pigments

EFFECT

Color acceptance with organic pigments



Color acceptance with inorganic pigments



Influence on coating properties



SUITABILITY

waterborne



solventborne



2-pack 100%



radiation-curing



● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Architectural paints
- Pigment concentrates

TECHNICAL DATA

acid value (as supplied)	Approx. 35 mg KOH/g
active matter content	100 %
amine value (as supplied)	Approx. 150 mg KOH/g
appearance	hazy liquid
chemical description	aminic surfactant

SOLUBILITY

Water	Ethanol
●	●
TPGDA	Mineral Spirits
●	●
● not soluble ● partly soluble ● soluble	

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.5 - 2.5 %

PROCESSING INSTRUCTIONS

- Add to the base paint.
- Addition to the grind or the let-down of the base paint possible.
- Post addition to the tinted paint possible.

HANDLING & STORAGE

12 months, when stored frost-free in unopened containers.

[MSDS & REGULATORY INFORMATION](#)



This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com