

Specialty filler

SIPERNAT® 820 A

DESCRIPTION

SIPERNAT® 820 A is a precipitated synthetic silicate with exceptionally bright clean color. SIPERNAT® 820 A has highly structured particles that provide film reinforcement, TiO₂ spacing, sheen uniformity, and excellent dry opacity.

KEY BENEFITS

- very good dry opacity
- very good gloss reduction
- improved washability and scrub resistance

EFFECT

Dry Opacity



Washability and scrub resistance



Gloss reduction



SUITABILITY

direct grind



solventborne



waterborne



● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- High PVC architectural interior paints
- High hiding wall primers
- DIY paints applied using brush, spray, or roller
- Low-sheen premium quality wall paints
- Breathable facade and concrete coatings

TECHNICAL DATA

delivery form	free-flowing powder
DOA absorption	155 ml/100g
loss on drying	7 %
particle size, d ₅₀	7 μm
pH value, 20% in water	10
sodium sulfate content	0.5 %
specific gravity	2.1 g/cm ³
specific surface area (BET)	85 m ² /g

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.5 - 5 %

PROCESSING INSTRUCTIONS

- It is recommended that this product be added, as supplied, to the grind.
- Addition into grind preferably before adding TiO₂.

HANDLING & STORAGE

This product is best used within 24 months of its manufacture. Evonik precipitated silicate products are extremely chemically stable. However, precipitated silicates including this product can absorb moisture and/or volatile organic compounds from the surrounding atmosphere. Therefore, we recommend storage in original sealed packaging and in a dry, cool place and removed from volatile organic substances. Even if a product is stored under these conditions, over periods of time the material may still pick up enough moisture to exceed the moisture content that is specified "as packaged" or at the time of packaging.

MSDS & REGULATORY INFORMATION



This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com